

## READILY BIODEGRADABLE HYDRAULIC FLUID

### Description:

EnviroLogic® 132 hydraulic fluid is a biodegradable and non-hazardous ISO 32 viscosity grade hydraulic oil for use in general purpose hydraulic systems. EnviroLogic® 132 is based on unique biodegradable base oil technology and is a direct replacement for petroleum oil based hydraulic fluids of the same viscosity. EnviroLogic® 132 is formulated with performance additive chemistry to exceed the requirements of petroleum hydraulic fluids. EnviroLogic® 132 is intended for use in applications with temperature requirements ranging from -30°F to 200°F and pressure requirements up to 5000 psi. EnviroLogic® has reduced environmental impact in the event of a leak or spill, as it is readily biodegradable and non-sheening.

EnviroLogic® 132 is self certified as an Environmentally Acceptable Lubricant (EAL) compliant with 2013 US EPA Vessel General Permit (VGP).

EnviroLogic® 132 is approved and / or meets specifications of:

- USDA BioPreferred\*
- The Stanley Works Company
- US Navy - Naval Hydraulic Tools
- MIL-PRF-32073A Grade III
- Nasatka Barrier
- Sauer Danfoss
- Jacobsen
- Allied Systems Co.
- Perry Slingsby Systems
- Dadee Manufacturing

Property	Method	Requirements	Result
Kinematic Viscosity	D445		
At 40°C, cSt		28.8 – 35.2	32
At 100°C, cSt		5.0 min	7.0
Viscosity Index	D2270	90 min	189
Density (60°F), kg/m <sup>3</sup>	D4052	Report	903
Density (60°F), lbs/gal	D4052	Report	7.52
API Gravity	D1298	Report	25.2
Pour Point, °C	D97	-15 max	-39
Flash Point (COC), °C	D92	185 min	205
Acid Number, mgKOH/g	D664	Report	0.30
Steel Pin Corrosion (24 hours, 100°C)	D665	Pass	
Deionized Water			Pass
Synthetic Salt Water			Pass
Copper Corrosion (3 hours, 100°C)	D130	2 max	1B

## 132 Readily Biodegradable Hydraulic Fluid

Property	Method	Requirements	Result
Foam Properties (after 10 minutes)	D892		
Sequence I, mL	Tendency-Stability	50-0 max	50-0
Sequence II, mL	Tendency-Stability	50-0 max	50-0
Sequence III, mL	Tendency-Stability	50-0 max	-0
Demulse Properties (54°C)	D1401		
Oil / Water / Emulsion		40 / 37 / 3	40 / 40 / 0
Minutes		30 max	30
Hydrolytic Stability	D2619		
Copper Weight Loss, mg/cm <sup>3</sup>			0.09
Change in Acid Number, mgKOH/g			0.09
Appearance of Copper Panel			1B
Four Ball Wear	D4172		
75°C/ 1200 rpm/ 40 kg/ 1 Hr., mm			0.58
Vickers 35VQ25 Vane Pump*	35VQ25		Pass
Vickers V104C Vane Pump*	ISO 20763		
Loss of ring, mg		120 max	1.9
Total loss of vanes, mg		30 max	4.8
Denison HF-6 Hybrid Pump*	T6H20C		
Total loss of pistons mg		300 max	186.7
Total loss of vanes and pins, mg		15 max	1.4
FZG (A/8.3/90), fail load*	D5182		10
Biodegradability	D7373	> 60	> 60
Ecotoxicity			
Fathead minnow, 96h LC50, ppm	OECD 203	> 100	> 10,000
Daphnia magna, 48h EC50, ppm	OECD 202	> 100	> 100
Algae, 72h EC50, ppm	OECD 201	> 100	> 100
Elastomer SRE-NBR-1 (100°C 168 hours)	D471	Pass	Pass
Elastomer HNBR (100°C 168 hours)	D471	Pass	Pass
Elastomer FKM (100°C 168 hours)	DIN 1817	Pass	Pass
Compatibility with Select Hydraulic Fluids			
Biodegradable Competitor stored @ 100°F		Pass	Pass
Biodegradable Competitor stored @ -5°F		Pass	Pass
Petroleum Hydraulic Fluid stored @ 100°F		Pass	Pass
Petroleum Hydraulic Fluid stored @ -5°F		Pass	Pass

\*based on read across from EnviroLogic® 146.

NOTICE: While this information is presented in good faith and believed to be accurate, RSC Bio Solutions does not guarantee satisfactory results from reliance thereon. The data is offered solely for your information and RSC Bio Solutions disclaims all liability for any loss or damage from its use. Thoroughly test any application according to the product directions and independently conclude satisfactory performance. Nothing contained herein is to be construed as a recommendation to use the product in violation of any patent.



Products you need  
for problems you don't.™

9609 Jackson Street  
Mentor, Ohio 44060  
800-661-3558  
rscbio.com

EnviroLogic® is a registered trademark of Terresolve Technologies, Ltd.  
Terresolve Technologies, Ltd. DBA RSC Bio Solutions.  
Copyright© 2014. RSC Bio Solutions. All Rights Reserved.