

## 200 READILY BIODEGRADABLE, INDUSTRIAL ISO 68 GEAR OIL

### Description

EnviroLogic® 200 is a readily biodegradable synthetic gear oil for use in industrial applications. EnviroLogic® 200 is an ISO 68 viscosity grade, AGMA 2EP oil, having high AW/EP properties, excellent corrosion and rust protection, and outstanding system cleanliness characteristics. The excellent performance characteristics of EnviroLogic® 200 make it suitable in a wide variety of industrial gear applications where incidental exposure of the oil to the environment is of concern. Examples are off-shore oil and gas, marine transportation & construction, steel milling, mining, and power utility operations. In the event of an oil spill or leak, the fluid biodegrades by more than 60% within 28 days, thereby minimizing any environmental impact.

EnviroLogic® 200 is self certified as an Environmentally Acceptable Lubricant (EAL) compliant with 2013 US EPA Vessel General Permit (VGP).

It meets or exceeds the following performance levels:

- Aegir
- AGMA 9005 (2 EP)
- AGMA 250.04/251.02 (2 EP)
- Berg
- Blohm + Voss
- Chesterton
- Cincinnati Milacron P-63
- David Brown S1.53.101
- DIN 51517, Part 3
- IHC Merwede
- James Walker
- Kamewa
- Kemel
- Ortlinghaus
- Schottel
- U.S. Steel 224
- Wartsila

Property	Method	Spec.	Result
Kinematic Viscosity	D445		
At 40°C, cSt		61.2 – 74.8	68
At 100°C, cSt			12
Viscosity Index	D2270		> 175
Density(60°F), g/cm <sup>3</sup>	D4052		0.84
Pour Point, °C	D97	-12 min.	-42
Flash Point (COC), °C	D92		185
Copper Corrosion 3 Hrs. @ 100°C	D130	1b min.	1b

Property	Method	Spec.	Result
Steel Pin Corrosion (4 hours, 140°F)	D665		
Deionized Water		Pass	Pass
Synthetic Salt Water		Pass	Pass
Foam Properties	D892		
Sequence I, mL	Tendency/Stability	50/0	50/0
Sequence II, mL	Tendency/Stability	50/0	50/0
Sequence III, mL	Tendency/Stability	50/0	50/0
Demulse Properties (54°C)	D1401		
Oil / Water / Emulsion			40 / 40 / 0
Minutes		30 max.	10
TOST Oxidation	D943		
Hours to TAN of 2.0 mg KOH/g			> 1500 ---
Air Release	D3427		
@ 90°C	9 max.		8.6
Four Ball EP	D2783		
Weld Load	250 min.		> 250
LWI, kg	45 min.		> 39
Four Ball Wear	D4172 Mod.		
54°C/1800 rpm/20 kg/1 Hr.	Scar, mm		0.22
Gear Oil Oxidation	D2893B		
Δ 100°C K.V. @ 312 Hrs.	6% max.		4.2%
Elastomer Compatibility			
Buna N (100°C 168 Hours)	D471		Pass
Viton (150°C 168 Hours)	D471		Pass
Biodegradability	D7373	60% min.	> 60
Ecotoxicity			
Fathead minnow	OECD 203	> 100mg/L	> 1000
Daphnia	OECD 202	> 100mg/L	mg/L
Algae	OECD 201	> 100mg/L	> 130 mg/L > 120 mg/L

NOTICE: While this information is presented in good faith and believed to be accurate, RSC Bio Solutions does not guarantee satisfactory results from reliance thereon. The data is offered solely for your information and RSC Bio Solutions disclaims all liability for any loss or damage from its use. Thoroughly test any application according to the product directions and independently conclude satisfactory performance. Nothing contained herein is to be construed as a recommendation to use the product in violation of any patent.



Products you need  
for problems you don't.™

9609 Jackson Street  
Mentor, Ohio 44060  
800-661-3558  
rscbio.com

EnviroLogic® is a registered trademark of Terresolve Technologies, Ltd.  
Terresolve Technologies, Ltd. DBA RSC Bio Solutions.  
Copyright© 2014. RSC Bio Solutions. All Rights Reserved.