

246 READILY BIODEGRADABLE, INDUSTRIAL ISO 460 GEAR OIL

Description

EnviroLogic® 246 is a readily biodegradable synthetic gear oil for use in industrial applications. EnviroLogic® 246 is an ISO 460 viscosity grade, AGMA 7EP oil, having high AW/EP properties, excellent corrosion and rust protection, and outstanding system cleanliness characteristics. In addition, it can directly replace petroleum oil based products of the same viscosity. The excellent performance characteristics of EnviroLogic® 246 make it suitable in a wide variety of industrial gear applications where incidental exposure of the oil to the environment is of concern. Examples are off-shore oil and gas, marine transportation & construction, steel milling, mining, and power utility operations. In the event of an oil spill or leak, the fluid biodegrades by 60% or more within 28 days, thereby minimizing any environmental impact.

EnviroLogic® 246 is self certified as an Environmentally Acceptable Lubricant (EAL) compliant with 2013 US EPA Vessel General Permit (VGP).

It meets or exceeds the following performance levels:

- Aegir
- AGMA 9005 (7 EP)
- AGMA 250.04/251.02 (7 EP)
- Berg
- Blohm + Voss
- Chesterton
- Cincinatti Milacron P-35
- David Brown S1.53.101
- DIN 51517, Part 3
- IHC Merwede
- James Walker
- Kamewa
- Kemel
- Ortlinghaus
- Schottel
- U.S. Steel 224
- Wartsila

Property	Method	Spec.	Result
Kinematic Viscosity At 40°C, cSt	D445	414.0 –	460
		506.0	
At 100°C, cSt			52
Viscosity Index	D2270		> 175
Density(60°F), g/cm ³	D4052		0.85
Pour Point, °C	D97	-9 min.	-39
Flash Point (COC), °C	D92		192

Property	Method	Spec.	Result
Copper Corrosion 3 Hrs. @ 100°C	D130	1b min.	1b
Steel Pin Corrosion (4 hours, 140°F)	D665		
Deionized Water		Pass	Pass
Synthetic Salt Water		Pass	Pass
Foam Properties	D892		
Sequence I, mL	Tendency/Stability	50/0	50/0
Sequence II, mL	Tendency/Stability	50/0	50/0
Sequence III, mL	Tendency/Stability	50/0	50/0
Demulse Properties (54°C)	D1401		
Oil / Water / Emulsion Minutes		30 max.	43 / 37 / 0 5
TOST Oxidation	D943		
Hours to TAN of 2.0 mg KOH/g			> 1500 ---
Air Release @ 90°C	D3427		22.0
Four Ball EP	D2783		
Weld Load	250 min.		> 250
LWI, kg	45 min.		> 48
Four Ball Wear	D4172 Mod.		
54°C/1800 rpm/20 kg/1 Hr.	Scar, mm		0.26
Timken Wear	D2782		
OK Load, lbs.	60 min.		75
Fail Load, lbs.	---		80
FZG	D5182		
Pass Stage	12 min.		14
Gear Oil Oxidation	D2893B		
Δ 100°C K.V. @ 312 Hrs.	6% max.		4.2%
Elastomer Compatibility			
Buna N (100°C 168 Hours)	D471		Pass
Viton (150°C 168 Hours)	D471		Pass
Biodegradability	D7373	60% min.	> 60
Ecotoxicity			
Fathead minnow	OECD 203	> 100mg/L	> 1000 mg/L
Daphnia	OECD 202	> 100mg/L	> 130 mg/L
Algae	OECD 201	> 100mg/L	> 120 mg/L

NOTICE: While this information is presented in good faith and believed to be accurate, RSC Bio Solutions does not guarantee satisfactory results from reliance thereon. The data is offered solely for your information and RSC Bio Solutions disclaims all liability for any loss or damage from its use. Thoroughly test any application according to the product directions and independently conclude satisfactory performance. Nothing contained herein is to be construed as a recommendation to use the product in violation of any patent.



Products you need
for problems you don't.™

9609 Jackson Street
Mentor, Ohio 44060
800-661-3558
rscbio.com

EnviroLogic® is a registered trademark of Terresolve Technologies, Ltd.
Terresolve Technologies, Ltd. DBA RSC Bio Solutions.
Copyright© 2014. RSC Bio Solutions. All Rights Reserved.