



READILY BIODEGRADABLE UNIVERSAL TRACTOR FLUID

Description:

EnviroLogic[®] 700 Universal Tractor Fluid is a readily biodegradable* ISO 46 tractor oil for use in heavy duty brake, transmission and hydraulic systems. EnviroLogic[®] 700 is based on natural ester technology and is a direct replacement for petroleum oil based tractor fluids of the same viscosity. EnviroLogic[®] 700 exceeds the requirements for petroleum oil based tractor fluids and has excellent anti-wear characteristics.

EnviroLogic® 700 is suitable for use where the following tractor specifications are required.

- Ford ESN-M2C134-D
- FHHA-2-C-201.00
- Case New Holland CNH MAT3525
- Case New Holland CNH MAT3505
- CASE MS 1209
- CASE MS 1207
- John Deere JDM 120C
- Massey Ferguson CMS M1145
- Massey Ferguson CMS 1143

Property	Method	Spec.	Result
Kinematic Viscosity	D445		
At 40°C, cSt	The state of the s	41.4 - 50.6	47
At 100°C, cSt		9.1 min.	11.2
Viscosity Index	D2270	N/A	>200
Density(60°F), Kg/m ³	D4052	N/A	900
Brookfield Viscosity @ -35°C, cps	D2983	70,000 max.	
			11,150
Pour Point, °C	D97	-36 min.	-40
Flash Point (COC), °C	D92	200 min.	220
JD Cold Flow Performance @ -35°C	JD 73	30 max.	27.0
Copper Corrosion	D130		
3 Hrs. @ 100°C		1b min.	1a
Steel Pin Corrosion (4 hours, 100°C)	D665B		
Synthetic Salt Water		Pass	Pass
Foam Properties	D892		
Sequence I, II, III	Tendency/Stability	Pass	Pass
Timken Wear	D2733		
OK Load, N.		N/A	73

Property	Method	Spec.	Result
Brake Noise and Capacity	Ford 6610	Pass	Pass
Power Shift Clutch Friction	JDQ 94	Pass	Pass
Brake Performance Test	JDQ 96	Pass	Pass
Brake Performance Test	Massey	Pass	Pass
	Ferguson		
Biodegradability, %	OECD 301B	>60	65
Aquatic Toxicity Daphnia, EC50 mg/L	OECD 202	>100	400
Aquatic Toxicity Bluegill, EC50 mg/L	OECD 203	>100	> 10,000

NOTICE: While this information is presented in good faith and believed to be accurate, RSC Bio Solutions does not guarantee satisfactory results from reliance thereon. The data is offered solely for your information and RSC Bio Solutions disclaims all liability for any loss or damage from its use. Thoroughly test any application according to the product directions and independently conclude satisfactory performance. Nothing contained herein is to be construed as a recommendation to use the product in violation of any patent.



Updated: 10/13/15

